

FK 777

Floor toppings

FK 777 is an **aliphatic polyurethane based clear floor top coating** for interior and exterior applications. It has excellent adhesion over epoxy and epu under coats.

Properties:

- Fast curing.
- Excellent UV resistance
- Good abrasion resistance.
- Used as top coat for terrazzo and decorative quartz floors.

Direction to use:

- Ensure that the surface to be top coated is smooth, zero levelled and free of any surface impurities.
- Mix FK 777 resin and FK 777 hardener in 1 : 1 ratio by volume.
- Agitate the mixture for 2-3 minutes.
- Apply by roller / brush.
- Allow to cure for 3-4 hours.
- Apply second coat.
- Allow to cure.
- Allow trafficking after 24 hours of curing.

Typical physical properties

Type	Polyester-aliphatic isocyanate
Mixing ratio (R : H)	1 : 1 by volume
Volume Solids	60%
Colour	Clear
Finish	Glossy
Flash point	Above 29° C
Surface dry	60-90 min.
Tack free dry	3-4 hours
Hard dry	24 Hrs
Pot life	60 - 90 min at 30° C
Theoretical Coverage	10-12 sqm. / litre @ 50 microns
Clean up	PUT 502
Shelf life	6 months in the unopened container.